

AF



(11) **EP 0 966 910 A1**


(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication: **29.12.1999 Bulletin 1999/52**
(51) Int. Cl.⁶: **A47J 36/02**
(21) Application number: **99111291.3**
(22) Date of filing: **10.06.1999**

<p>(84) Designated Contracting States: AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE Designated Extension States: AL LT LV MK RO SI</p> <p>(30) Priority: 24.06.1998 US 90567 15.12.1998 US 211749</p> <p>(71) Applicant: Clad Metals LLC Canonsburg, PA 15317 (US)</p>	<p>(72) Inventor: Groll, William A. McMurray, Pennsylvania 15317 (US)</p> <p>(74) Representative: Türk - Gille - Hrabal - Struck Patentanwälte - European Patent Attorneys, Brucknerstrasse 20 40593 Düsseldorf (DE)</p>
--	--

(54) **Stick resistant coating for cookware**

(57) A method for making a stick resistant cook surface or cooking vessel having the stick resistance in which a hard substrate metal (6) is buffed/polished to a high luster surface finish of less than 20 micro inches and then coated with a layer of zirconium nitride (20). The method further includes the step of polishing a stamped blank to the desired surface smoothness prior to the drawing/shaping step to provide a stick resistant surface in cooking vessels having side walls, such as pots and pans, which are otherwise difficult to buff in the interior due to the side wall geometry.



EP 0 966 910 A1

Description

BACKGROUND OF THE INVENTION5 1. Field of the Invention

[0001] This invention relates generally to cookware and, more particularly, to cookware having a stick resistant coating applied thereto.

10 [0002] Heretofore, it has been common to apply a lubricative layer of PTFE (polytetrafluoroethylene) to the cooking surface of metal cookware to provide, at least initially, a relatively stick-free surface. Over time, the PTFE loses lubricity and becomes less stick-free or somewhat stick resistant. The PTFE surface is somewhat objectionable because much softer than the metal substrate and is easily scratched and otherwise marred by metal spatulas, forks and other kitchen utensils used for cooking. Once scratched or otherwise marred, the PTFE surface can be chipped off and generally loses its original utility as a stick-free surface.

15 2. Description of the Related Art

[0003] More recently, attempts have been made, as disclosed in UK Patent Application GB 2,277,466A to Tsai, to increase the scratch resistance of PTFE. Other work in the area aimed at improving the hardness and durability of stick resistant coatings for cookware is embodied in U.S. Patent No. 5,447,803 to Nagaoka et al., which discloses a coating of titanium nitride to steel fry pans. The TiN coating is applied by physical vapor deposition (PVD) or by chemical vapor deposition (CVD) and then heat treated in an atmosphere consisting of oxygen and nitrogen in a controlled ratio to form a protective layer of titanium oxide on the surface of the titanium nitride layer. The titanium nitride layer is said to be hard and, in addition, produces a pleasing golden color to improve the appearance of the fry pan.

25 [0004] Zirconium nitride is a known ceramic coating which has been applied to enhance hardness and wear resistance to various industrial goods such as drill bits, lathe bits and injection molds.

[0005] I have discovered that zirconium nitride provides an excellent long-lasting, stick resistant coating for cookware when the substrate metal is properly selected and prepared. In addition, zirconium nitride does not require a separate treatment step to produce an oxide surface as is necessary with prior titanium nitride surfaces. Further, the zirconium nitride coating of my invention provides a pleasing golden color on the cookware which does not discolor when exposed to direct flame, which occurs with titanium nitride coatings. The zirconium nitride coating of the present invention is extremely hard and abrasion resistant, which provides a durable, long-lasting, stick resistant cooking surface, thus making it particularly suitable for restaurant and institutional kitchens. The pleasing gold tone color of the zirconium nitride coating, coupled with its stick resistant properties on the cookware of the present invention, likewise, makes it suitable for the houseware consumer market.

SUMMARY OF THE INVENTION

40 [0006] The present invention is directed to a cooking or baking surface, hereinafter referred to collectively as "cook surface", having a stick resistant coating of a ceramic nitride material, preferably zirconium nitride, thereon. The invention also relates to a method of making the coated cook surface, as well as to the resultant cooking or baking vessels made by the method.

45 [0007] Briefly stated, the cook surface of the invention comprises a hard substrate metal such as stainless steel, carbon steel, titanium or the like, which is buffed to a high luster finish of less than 20 micro inches, preferably in the range of 9-12 micro inches, and still more preferably about 2-6 micro inches. The buffed surface of the substrate metal is cleaned and then coated with the preferred material, zirconium nitride. There is no need to heat treat the applied coating to produce a protective oxide layer, since zirconium nitride is self-passivating in the atmosphere and, thus, forms a protective layer of zirconium oxide without any special treatment.

50 [0008] The substrate metal of the cooking vessel can be a single layered material or it may be bonded as a clad composite to layers of various other metals such as a conductive core material, for example, copper or aluminum, to promote thermal conductivity. Magnetic layers of ferritic stainless steels may also be included in the composite to make the vessel compatible with induction heating ranges.

55 [0009] When the substrate metal is part of a clad composite of various metal layers, as described above, the zirconium nitride coating is preferably applied by the cathodic arc method known in the art as the physical vapor deposition method (PVD). This method uses a vacuum chamber pressure on the order of 10^{-5} Torr at a temperature of about 500° - 900°F. This temperature range promotes good coating adhesion while staying below the temperature at which stainless steel and aluminum (forming the clad composite) separate.

[0010] According to a preferred method according to the invention, when making deep drawn cooking vessels, such

as pots and certain pans, it is difficult to buff or polish the entire interior surface to a bright luster finish. In such circumstances, a presently preferred method of the invention comprises the step of forming a flat blank of the substrate metal, in a clad composite form, if applicable, then buffing the cooking surface of the flat blank to a high luster finish and then drawing the thus-polished blank to a desired shape of the finished vessel. The shaped vessel is then cleaned and the buffed surface is coated with the zirconium nitride material to provide a stick resistant surface.

[0011] These features, as well as other advantages and attributes of the invention, will become more readily apparent when reference is made to the drawings when taken with the following detailed description.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012]

Fig. 1 is an enlarged cross-sectional side view of a clad metal composite of a stick resistant cook surface according to the present invention; and

Fig. 2 is a view similar to Fig. 1 but merely showing a single substrate metal layer having a stick resistant cook surface according to the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0013] With reference to the drawings, a multi-layer, or -ply, clad metal composite cook surface of the invention, generally designated by reference number 2, is shown. A single layer cook surface 4 is depicted in Fig. 2, which is also suitable in the practice of the present invention.

[0014] The multi-ply composite 2 of Fig. 1 having a stick resistant layer 20 thereon may comprise a substrate metal layer 6 at the cook surface of, for example, stainless steel, such as 304 grade. A heat conductive core layer 8 of Alclad Aluminum or copper or copper alloy is bonded to the substrate metal layer 6 and an exterior layer 10 of stainless steel is bonded to the core layer 8. The exterior layer 10 may be a 304 grade stainless steel or it may be a magnetic or ferritic grade 436, making the composite 2 suitable for use on an induction heating range, as well as a conventional gas or electric radiant heating range.

[0015] The multi-ply composite 2 of Fig. 1 may also represent a flat griddle plate wherein the substrate metal layer 6 and exterior layer 10 are of stainless steel and the core layer 8 is copper or copper alloy. The zirconium nitride stick resistant layer 20 provides excellent properties for a commercial griddle plate.

[0016] The substrate metal layer 12 of Fig. 2 forms the entire cross section of the cook surface and may be in the form of a griddle plate, grill grate or other cookware. It is well-known, however, in the cooking art that multi-ply composite metals having high thermal conductivity cores, of the type depicted in Fig. 1, offer superior cooking performance when used in cooking vessels such as pots, pans and oven bakeware.

[0017] The substrate metal layers 6 or 12 must be highly compatible with the thermal expansion properties of the stick resistant layer 20 of zirconium nitride of Fig. 1 or 20' of Fig. 2. Otherwise, the zirconium nitride coating will not adhere properly. The substrate metal layer should also be a hard metal. Preferred substrate metals include titanium or any of a wide variety of grades of stainless steel, including the above grades 304 and 436. A soft material such as aluminum or copper should be avoided for use as a substrate metal layer 6 or 12.

[0018] In order to provide superior stick resistant properties, the interior surface, i.e., the substrate metal layer 6 or 12, must be finished by fine polish grinding preferably followed by buffing to a high surface smoothness, providing a bright luster finish. As the substrate metal surface smoothness increases, the stick resistant properties of the stick resistant layer 20 and 20', likewise, increase. The surface preparation preferably involves a two-step grinding operation carried out on a commercial device, known as a Hi-Lite brand buffing machine, using a 180 grit alumina abrasive paper flooded with a petroleum based lubricant. A stationary nose of the machine carries the abrasive while the metal substrate is spun at speeds of 500 to 1,000 rpm. The nose carrying the abrasive traverses the spinning metal two times. The metal is then further treated using a finer abrasive of 220 grit using the same machine parameters as above, also employing a double traverse. The treated surface has a bright luster finish of less than 20 micro inches and preferably 10-16 micro inches, more preferably, an ultra bright surface finish of 2-6 micro inches with a surface smoothness of 3 micro inches being superior. It is, of course, understood that a higher luster surface requires additional polishing with a buffing wheel and medium buffing abrasive which adds some additional cost to the finished cookware. Thus, a compromise between added cost and added stick resistance must be made in a commercial setting.

[0019] The applied zirconium nitride forming stick resistant layer 20, 20' provides a cosmetically pleasing gold color to the cookware and, thus, in addition to the stick resistant layers 20, 20', the zirconium nitride may be applied as an exterior decorative layer 30 and 30', Figs. 1 and 2, respectively. The exterior surfaces of the underlying exterior metal layer need not be buffed to the high degree of smoothness required on the cook surface since stick resistance is not required on the exterior surfaces of the cooking vessel. Of course, it is understood that the zirconium nitride can be

applied to selected surfaces of the cookware to achieve any desired appearance, simply by masking those surfaces which are not to be coated. These masking techniques are well-known in the coating art.

[0020] A high degree of surface cleanliness is required prior to coating the metal substrate layer. The dirty areas will act as a mask and prevent adhesion of the layers 20, 20', 30, 30'. The surface is cleaned with a detergent and rinsed with deionized water after the buffing/polishing treatment, then later cleaned further in an ultrasonic bath.

[0021] The zirconium nitride applied to the cooking vessel is done by the cathodic arc method also known as the physical vapor deposition method (PVD). In the case of clad material, the PVD method is employed. This method uses a vacuum chamber pressure of about 10^{-5} Torr and a temperature of 500° - 900°F. This temperature range promotes good coating adhesion while staying under the temperature at which the stainless steel and aluminum layers in the clad composite would separate. The parts to be coated are first cleaned with a plasma bombardment of an inert gas. This initial bombardment activates the surface by reducing the surface oxide. The zirconium is then vaporized and a layer which is several angstroms thick is deposited on the surface. A nitrogen atmosphere is then introduced and the zirconium nitride ceramic of layer 20, 20' or 30, 30' is built. The cycle is completed when a measured amount of oxygen is introduced into the chamber and a zirconium oxide layer is formed. A coating thickness of one and one-half to three microns is achieved for layer 20, 20'. A preferred thickness for a stick resistant layer of zirconium nitride is two microns.

[0022] Zirconium nitride offers a number of significant advantages over the known titanium nitride material. The zirconium nitride can be applied to a substrate at a lower temperature range than that required for titanium nitride. This is particularly beneficial in the case of bonded metals which separate or distort at higher temperatures. In addition, titanium nitride can react galvanically with the substrate, causing surface degradation, discoloration and corrosion. Because of a higher deposition rate, zirconium is more economical to apply. Zirconium exhibits a self-passivating characteristic which tends to prevent galvanic current paths from forming. U.S. Patent No. 5,447,803 of Nagaoka et al. teaches a final back flushing of oxygen to stabilize the surface with a layer of titanium oxide. This layer can be chemically or abrasively damaged, which leaves the titanium/substrate system susceptible to galvanic corrosion.

[0023] In conclusion, zirconium nitride, when applied as a surface coating to cookware, bakeware, grills, griddles or other food preparation surfaces offers: (a) a high durable wear resistance; (b) high corrosion resistance; and (c) substantial resistance to sticking of foods to the surface.

[0024] Zirconium nitride is superior to PVD or CVD deposited titanium nitride for the following reasons: (a) zirconium nitride can be applied at a lower temperature than titanium nitride; (b) zirconium nitride is self-passivating, which offers superior corrosion resistance. Titanium nitride has far less tendency to form an oxide after the initial coating treatment; and (c) zirconium nitride can be applied more economically than titanium nitride. Thus, zirconium nitride offers a superior stick resistant layer 20, 20' over the previously proposed titanium nitride coatings of the prior art.

[0025] I have found that it is difficult to uniformly buff the bottom cooking surface of deep drawn cookware, such as pots, when applying an ultra high luster finish (2-4 micro inches), since the high walls of the vessel interfere with the entry of the buffing wheel. Accordingly, in the manufacture of deep drawn cookware, according to the present invention, I have found it advantageous to first polish and buff the flat metal blank to a smooth, high or ultra high luster finish prior to subjecting the blank to a drawing operation for forming the cookware vessel. The polished/buffed surface of the blank remains substantially undisturbed during the drawing operation and may then be coated with titanium nitride (after appropriate cleaning).

Comparative Tests

Test I - Surface Smoothness

[0026] A first multi-ply clad fry pan comprising an interior substrate metal layer (cook surface) of 304 stainless steel, a core layer of Alclad Aluminum and an exterior surface layer of 436 stainless steel was made in a conventional manner and then subjected to the titanium nitride coating process. Before coating, the exterior surface of the fry pan was buffed to a bright luster and the interior surface was finished with a concentric pattern known in the industry as a "Hi-Lite" finish using a lubricated 150 grit abrasive. A second fry pan of the same size and multi-layer clad composition was made and then aggressively buffed using a hard cloth buff wheel and a medium buffing compound on the interior and exterior surfaces, bringing both surfaces to an ultra high reflective luster finish of about 3 microns and then subjected to the same titanium nitride coating process as the first fry pan. Both coated pans were compared to an uncoated multi-ply stainless steel third fry pan in a standard objective test, which involved burning a measured sample of brown sugar and water on the cook surface of the fry pans. Both the first and second titanium nitride coated pans clearly exhibited better release properties than the bare, uncoated multi-ply stainless steel third fry pan. However, the second fry pan that had the higher luster buffed interior prior to titanium nitride coating showed better release characteristics than the abrasively finished first fry pan. A buffed, bright luster surface finish suitable for subsequent titanium nitride coating in accordance with my invention thus preferably has a surface smoothness of about 3 micro inches. By way of comparison, the surface finish of the above-mentioned "Hi-Lite" finish had a surface smoothness on the order of about 9-12

micro inches.

[0027] This comparative test thus demonstrates that a smoother surface on the substrate layer provides improved stick resistance properties in the ceramic nitride layer.

5 Test II - Egg Cooking Cleanup

[0028] A standard ten-inch diameter stainless steel-aluminum core-stainless steel fry pan was tested against an identically constructed pan but having a 1.5 micron thick coating of zirconium nitride on the stick resistant layer 20 and also applied on the exterior surface 30. A release additive, Pam[®], was sprayed briefly on each pan and an egg was then fried in each. After cooking, the pans were cleaned using a scrub pad and rated with an assigned value of 1 to 5, with 1 being rated the best and 5 the worst. Five cooking trials were run on each pan. The stainless steel standard fry pan rated an average 3 in cleanability while the zirconium nitride coated stainless pan rated an average 1.2, which is considered excellent and actually equivalent to a new, non-stick PTFE surface.

15 Test III - Coating Thickness

[0029] The purpose of this test was to find out how well the release properties of the ZrN of various thicknesses hold up with use.

[0030] The experiment tested the release properties of two stainless steel aluminum core fry pans having different thicknesses of zirconium nitride thereon. The first pan had 0.56 microns of ZrN while the second pan had a 2 micron thick layer of ZrN thereon. The pans were put through a baked bean scrape/wash test. One tablespoon of Bush's Best Baked Beans was placed in the center of each pan and heated until all of the syrup had turned into a black residue. Then a spoon was dragged across the burnt beans. The success of the scrape was recorded on a scale of 1 to 5 as follows:

- 1 = All beans come off the pan with the scrape
- 2 = Beans flake off in large chunks
- 3 = Beans are removed from the path of the spoon only
- 4 = Most, but not all, beans are removed from the path of the spoon
- 5 = No beans are removed.

[0031] After recording the value for the scrape, the pan was soaked for one minute in hot water and Palmolive[®] dish detergent. After soaking, the pan was washed with a scrubbing pad and another rating was assessed using the same scale. Some of the tests left a silver stain on the pan. A scrubbing and polishing compound, Bar Keepers Friend[®], was used to remove the stain, so it would not be confused for a weak area in the coating.

[0032] The first pan tested having a ZrN coating thickness of 0.5 microns failed in its stick resistant properties after ten trials and bare stainless began to appear along the cook surface. The second pan tested, having a zirconium nitride layer of 2 microns in thickness, successfully completed 60 trials without failure.

[0033] The scrape test and soak/cleaning test results for the second pan are set forth below in tables (a)-(c) covering bean cooking trials 1-60.

Baked Beans Scrape/Wash Test on Batch 4 Pan 3										
Trials										
(a)				(b)				(c)		
Trials	Scrape	Wash		Trials	Scrape	Wash		Trials	Scrape	Wash
1	4	2		21	3	1		41	4	4
2	3	4		22	4	2		42	5	2
3	3	2		23	3	2		43	4	3
4	3	2		24	4	1		44	4	3
5	4	1		25	3	3		45	4	3
6	4	1		26	4	2		46	4	2

(continued)

Baked Beans Scrape/Wash Test on Batch 4 Pan 3 Trials										
(a)				(b)				(c)		
Trials	Scrape	Wash		Trials	Scrape	Wash		Trials	Scrape	Wash
7	4	1		27	3	1		47	4	3
8	4	1		28	3	2		48	4	3
9	4	1		29	4	1		49	3	3
10	4	1		30	3	3		50	5	3
11	3	2		31	4	3		51	4	4
12	3	3		32	5	3		52	4	3
13	4	1		33	5	3		53	4	3
14	4	1		34	4	3		54	3	2
15	3	2		35	4	3		55	4	4
16	3	2		36	4	2		56	4	4
17	3	1		37	3	2		57	4	2
18	3	2		38	3	3		58	4	3
19	4	1		39	5	3		59	4	3
20	3	2		40	5	3		60	4	4

[0034] While specific embodiments of the invention have been described in detail, it will be appreciated by those skilled in the art that various modifications and alternatives to those details could be developed in light of the overall teachings of the disclosure. The presently preferred embodiments described herein are meant to be illustrative only and not limiting as to the scope of the invention which is to be given the full breadth of the appended claims and any and all equivalents thereof.

Claims

1. A stick resistant cook surface comprising:

a substrate metal selected from the group consisting of stainless steel, carbon steel and titanium, said substrate metal surface having a bright luster finish of less than 20 micro inches, and
a layer of a ceramic nitride applied on the substrate metal.

2. The cook surface of claim 1 wherein the ceramic nitride is zirconium nitride.

3. The cook surface of claim 1 in a cooking device selected from the group consisting of stove-top cookware, oven bakeware, griddle plates and grill surfaces.

4. The cook surface of claim 1 used in one of a stove-top cookware vessel and an oven bakeware vessel, wherein said vessels having a layer of said zirconium nitride applied on at least an inner cooking or baking surface and on at least selected outer surfaces of said vessels.

5. A method for making a cook surface comprising the steps of:

providing a substrate metal selected from the group consisting of stainless steel, carbon steel and titanium;
forming a bright luster finish on said substrate surface of less than 20 micro inches;
cleaning the substrate; and
applying a coating of zirconium nitride to the bright luster finished substrate surface.

6. The method of claim 5 wherein the finish step comprises two finishing treatments, wherein a second of said treatments employs a finer polishing abrasive than used in a first of said polishing treatments.
- 5 7. The method of claim 5 including a third finishing treatment comprising buffing with a buffing wheel and a buffing abrasive compound.
8. The method of claim 5 wherein the substrate metal forms an outer layer of a multi-layered metal composite.
9. A method for making a cooking utensil comprising the steps of:
- 10 providing a metal sheet;
stamping a flat blank from the sheet metal substrate;
forming a bright luster finish on said blank;
drawing said bright luster finished blank to shape a cooking utensil of a desired configuration; and
15 applying a layer of zirconium nitride to at least a cooking surface of said cooking utensil.
10. The method of claim 9 wherein the cooking utensil is one of a fry pan, saucepan, saucier, casserole, saute pan, stock pot, brazier pan, stir fry pan and omelet pan.
- 20 11. The method of claim 9 wherein the metal sheet is a multi-layered metal composite sheet having an outer layer of stainless steel and an inner core layer of a high heat-conductive metal or metal alloy comprising one selected from the group consisting of aluminum and copper.
- 25 12. A cooking utensil comprising a shaped metal vessel having an outside surface and an inside surface, wherein said inside surface has a food contacting cook surface comprising a stainless steel having at least a bright luster surface finish of less than 20 micro inches or smoother, coated with a layer of zirconium nitride of a thickness of at least 2 microns.
- 30 13. The cooking utensil of claim 12 which is one of a stove-top cooking utensil and an oven baking utensil.
14. The cooking utensil of claim 13 which is an oven baking utensil wherein the stainless steel cook surface has an ultra bright surface finish of 2-4 micro inches coated with a layer of zirconium nitride.




Fig. 1




Fig. 2



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 11 1291

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
D,X	US 5 447 803 A (NAGAOKA) 5 September 1995 (1995-09-05) * column 2, line 53 - column 3, line 62; figures 1,2 *	1,3	A47J36/02
A	---	4,5,9, 10,12,13	
A	EP 0 416 887 A (NIPPON STEEL CORPORATION) 13 March 1991 (1991-03-13) * page 2, line 24 - page 4, line 48 *	1,5,9,12	
A	DE 31 42 312 A (DEGUSSA AG) 5 May 1983 (1983-05-05) * page 3, line 9 - page 4, line 20; figures *	1,3,5, 8-10, 12-14	
P,X	EP 0 870 458 A (THERMOCOMPACT) 14 October 1998 (1998-10-14) * page 3, line 17 - line 55; figures *	1,3,5,9	TECHNICAL FIELDS SEARCHED (Int.Cl.6) A47J B05D C23C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 22 September 1999	Examiner Bodart, P
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.82 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 11 1291

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-09-1999

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5447803	A	05-09-1995	JP 2041493 C	09-04-1996
			JP 4066667 A	03-03-1992
			JP 7074448 B	09-08-1995
			AU 648258 B	21-04-1994
			AU 6053190 A	23-01-1992
			CA 2065303 A	30-12-1991
			CN 1057867 A	15-01-1992
			DE 69026619 D	23-05-1996
			DE 69026619 T	28-11-1996
			EP 0489914 A	17-06-1992
			WO 9200032 A	09-01-1992
EP 416887	A	13-03-1991	JP 2619838 B	11-06-1997
			JP 3097865 A	23-04-1991
			DE 69018170 D	04-05-1995
			DE 69018170 T	27-07-1995
			US 5427843 A	27-06-1995
DE 3142312	A	05-05-1983	NONE	
EP 870458	A	14-10-1998	FR 2760621 A	18-09-1998

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82